

Technical Data Sheet

Ultrasint PA6 black

Components

BASF Polyamide 6-based powder for Laser Sintering

Product Description

All Ultrasint PA6 grades have in common that they show high modulus, high strength and excellent thermal distortion stability. These properties ensure precise feature control, very good mechanical properties and simple surface reprocessing of 3D printed parts.

Ultrasint PA6 black can fulfill the requirements of functional applications regarding high accuracy and mechanical strength as well as a high heat distortion temperature – properties, where existing 3D printing materials often show limitations.

Delivery form and warehousing

Ultrasint PA6 black powder should be stored at 15 - 25°C in its originally sealed package in a clean and dry environment.

Product safety

Mandatory and recommended industrial hygiene procedures and the relevant industrial safety precautions must be followed whenever this product is being handled and processed. Product is sensitive to humid environment conditions. For additional information please consult the corresponding material safety data sheets.

For your information

Ultrasint PA6 black comes in solid black color. Electrical properties (e.g. volume resistivity, surface resistivity), chemical properties (e.g. resistance against particular substances) and tolerance for solvents are available upon request. Generally, these properties correspond to publicly available data on polyamides.

Notice

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact BASF directly at 3d-printing@basf-3dps.com.

Contact: 3d-printing@basf-3dps.com

Continued page 2

Technical Data Sheet

Ultrasint PA6 black



We create chemistry

General Properties	Test method	Typical values
Bulk Density / kg/m ³	DIN EN ISO 60	490
Printed Part Density / kg/m ³	DIN EN ISO 1183-1	1150
Mean particle size d ₅₀ / μm	Laser Diffraction	65-75
Melting Temperature / °C	ISO 11357	220
Crystallization Temperature / °C	(20 K/min)	174
Melt Volume Flow Rate / cm ³ /10min	ISO 1133 (240 °C, 2.16 kg)	24

Mechanical Properties	Test method	Typical values x-direction		Typical values z-direction	
		dry ¹	cond. ²	dry ¹	cond. ²
Tensile Strength / MPa	ISO 527-2	61	54	47	43
Tensile Modulus / MPa		3500	1550	3550	1600
Tensile Elongation at break / %		1.9	51	1.4	6.0
Flexural Strength / MPa	DIN EN ISO 178	131	53	79	53
Flexural Modulus / MPa		3300	1550	3500	1650
Flexural Elongation at break / %		6.0	6.1	2.2	6.1
Charpy Impact Strength (notched) / kJ/m ²	ISO 179-1	2.5	4.2	1.7	2.8
Charpy Impact Strength (unnotched) / kJ/m ²		7.1	12.6	4.1	6.5
Izod Impact Strength (notched) / kJ/m ²	ISO 180	3.7	5.4	2.6	2.9
Izod Impact Strength (unnotched) / kJ/m ²		7.0	11.5	4.5	6.5

Thermal Properties	Test method	Typical values ¹
HDT/A (1.8 MPa) / °C	ISO 75-2	98
HDT/B (0.45 MPa) / °C		194
Vicat/A (10 N) / °C	ISO 306	216
Vicat/B (50 N) / °C		199

Contact: 3d-printing@basf-3dps.com

1) measured after drying 14 days at 80 °C / vacuum. Water content is about 0.07 % acc. to DIN EN ISO 15512.

2) measured after conditioning 14 days at 70 °C / 62 % r.h. Water content is about 2.5 % acc. to DIN EN ISO 15512.

All values measured with virgin material.