

## Technical Information

TI/N-CPN/IP Palamoll® 656  
June 2019

Page 1 of 4

Supersedes edition dated April 2016

## Petrochemicals Plasticizers



# Palamoll® 656

High viscosity polymeric plasticizer that is compatible with PVC. Resistant to oils, fats, aliphatic hydrocarbons and water. It has only a slight tendency to migrate into plastics and adhesives.

<b>Product Number</b>	50000030 bulk 50000350 drums
<b>BASF Registered Name</b>	Palamoll® 656
<b>CAS No.</b>	208945-12-4
<b>Average Molecular Weight</b>	6700

### Product Specifications

	Value	Test Method
Specific Gravity @ 25°/25 °C	1.079 - 1.099	ASTM D-4052
Viscosity @ 25 °C, cP	7,000 - 10,000	ASTM D-445
Acid Number, mg KOH/g (maximum)	1.5	ASTM D-1045
Water, by weight (% maximum)	0.1	ASTM E-203
Color, Pt-Co Units (APHA, maximum)	150	ASTM D-5386
Refractive Index n <sup>25</sup> <sub>D</sub>	1.467 - 1.470	ASTM D-1045
Suspended Matter	COLSFFM*	visual

\*Clear Oily Liquid Substantially Free of Foreign Material

## Typical Physical Properties

The following data were measured in the BASF Corp. laboratory. They do not represent any legally-binding guarantee of properties for our sales product

	Value	
Vapor Pressure @ 20 °C, mbar	< 0.1	
Storage Temperature, minimum, °C	>30	
Pour point, °C	-18	
Solubility @ 25 °C in water, mg/L	< 0.1	
	Dynamic viscosity [cP]	Density [g/cm <sup>3</sup> ]
@ 10 °C	26,200	1.101
@ 20 °C	11,400	1.093
@ 40 °C	2,990	1.078
@ 60 °C	1,060	1.063
@ 80 °C	469	1.048
Ignition Temperature, °C	425	
Flash point (COC), °C	274	
Odor	mild characteristic	
Surface Tension, mN/m,	30.8	
Solution Temperature, °C,	158	
Plastisol Gelation Temperature, °C	139	

**Description**

Palamoll® 656 is a high viscosity polymeric plasticizer that is compatible with PVC. It is based on adipic acid and polyhydric alcohols. It is resistant to oils, fats, aliphatic hydrocarbons and bitumen. It is soluble in organic esters, ketones, ethers, aromatic and chlorinated hydrocarbons.

**Applications**

Palamoll® 656 demonstrates low migration into other plastics or adhesives. It is highly resistant to animal, mineral and vegetable fats and oils and is used for protective aprons, gloves and boots. It is used in roofing systems and expansion joint tapes where bitumen, water and sunlight resistance is important. Palamoll® 656 is used in films that are coated with an adhesive such as electrical tape, decals and decorative film. It should be pre-heated to 80 °C before addition to the blender. The mixing cycle should continue until a temperature of 150 - 170 °C is reached, depending on the amount of plasticizer. It has a higher molecular weight than monomeric plasticizers and must be processed at a higher fusion temperature.

**Safety**

Based on toxicity studies, Palamoll® 656 has a low order of toxicity and does not require special handling. Handle in accordance with good industrial hygiene and safety practices. Avoid eye contact by wearing personal protective equipment. If eye contact occurs, wash with flowing water and contact physician.

Avoid repeated or prolonged skin contact. Avoid breathing vapors by providing adequate ventilation.

Always refer to the Safety Data Sheet (SDS) for detailed information on safety.

**Storage and Handling**

Palamoll® 656 can be stored for one year at temperatures below 40°C, if moisture is excluded.

If Palamoll® 656 is stored below 20 °C or for a long time at room temperature, it can become wax-like, cloudy and even solidify. This does not affect the properties of the ester. Upon reheating to 30 °C, Palamoll® 656 returns to a liquid state and conforms to its product specifications

**Packaging**

Palamoll® 656 is available in bulk tank trucks or drums.

**Contact Information****Marketing**

BASF Corporation  
11750 Katy Freeway, Suite 120  
Houston, TX 77079, USA

Tel: +1 800-533-8961  
Fax: +1 713-759-3036  
E-mail: [plasticizers@basf.com](mailto:plasticizers@basf.com)

**Technical Support**

BASF Corporation  
4403 La Porte Highway 225  
Pasadena, TX, 77501, USA

Tel: +1 281-884-4473 or -4432  
Fax: +1 281-884-4302

**Visit us online at**

<http://www.plasticizers.basf.com>

**Note**

---

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© 2019 BASF Corporation