Acrylic & Methacrylic Monomers

BASF
We create chemistry

Product [CAS no.]	C^{14} BIO-based content	Chemical Structure	Polymer Tg [°C]	Bp [°C]	**Coatings** *(Automotive / Industrial)*	**Emulsions** *(Coatings / Adhesives)*	**Adhesives & Sealants**	**Paper**	**Leather / Textile**	**Oilfield**	**Lubricants**	**Construction**	**Rubber / Plastics**	**Rad / UV Cure**
Alkyl Acrylates														
n-Butyl Acrylate (BA) [141-32-2]			-48	148	x	x	x	x	x			x	x	
2-Ethylhexyl Acrylate (2-EHA) [103-11-7]			-58	216	x	x	x	x	x			x	x	
Ethyl Acrylate (EA) [140-88-5]	✓		-24	99,8		x	x	x	x			x	x	
Methyl Acrylate (MA) [96-33-3]			-10	80,1		x	x					x	x	
iso-Butyl Acrylate (IBA) [106-63-8]			-24	138	x	x	x	x	x			x	x	
tert-Butyl Acrylate (TBA) [1663-39-4]			50	119	x	x	x	x	x			x	x	
2-Propylheptyl Acrylate (2-PHA) [149021-58-9]			-67	250	x	x	x						x	x
iso-Decyl Acrylate F (IDA F) [1330-61-6]			-58	158 (66 mbar)	x	x	x							x
Heptadecyl Acrylate (C17A) [1473386-36-5]			-64	-	x		x		x		x		x	x
Lauryl Acrylate 1214 F (LA 1214 F) [2156-97-0] (C12); [21643-42-5] (C14)	✓	 n = 12, 14	-	296	x	x	x	x	x	x	x			x
Lauryl Acrylate 12 F (LA 12 F) [2156-97-0]	✓		-	296	x	x	x	x	x	x	x			x
Stearyl Acrylate 1618 (SA 1618) [13402-02-3] (C16); [4813-57-4] (C18)	✓	 n = 16, 18	-	160 (3 mbar)	x		x		x	x	x			x
Stearyl Acrylate 18 (SA 18) [4813-57-4]	✓	 n = 18	-	160 (3 mbar)	x		x		x	x	x			x
Behenyl Acrylate 1822 F (BEA 1822 F) [4813-57-4] (C18); [48076-38-6] (C20); [18299-85-9] (C22)]	✓	 n = 18, 22	-	410	x		x		x	x	x			x
Behenyl Acrylate 22 F (BEA 22 F) [18299-85-9] (C22)	✓		-	410	x		x		x	x	x			x
Alkyl Methacrylates														
tert-Butyl Methacrylate (TBMA) [585-07-9]			107	136	x	x	x		x	x			x	
Cyclohexyl Methacrylate (CHMA) [101-43-9]			105	94 (20 mbar)	x	x	x		x		x	x	x	x
2-Ethylhexyl Methacrylate (2-EHMA F) [688-84-6]			-10	228	x	x	x		x		x		x	
iso-Decyl Methacrylate (IDMA) [29964-84-9]			-30	263	x		x				x			
Isotridecyl Methacrylate (C13MA) [85736-97-6]			-31	-	x		x				x			

Product [CAS no.]	C^{14} BIO-based content	Chemical Structure	Polymer Tg [°C]	Bp [°C]	Coatings (Automotive / Industrial)	Emulsions (Coatings / Adhesives)	Adhesives & Sealants	Paper	Leather / Textile	Oilfield	Lubricants	Construction	Rubber / Plastics	Rad / UV Cure
Alkyl Methacrylates														
Lauryl Methacrylate 1214 F (LMA 1214 F) [142-90-5] (C12); [2549-53-3] (C14)		 n = 12, 14	-50	308	x	x	x		x	x	x			
Lauryl Methacrylate 1215 F (LMA 1215 F) [90552-02-6]		 n =12, 13, 14, 15	-	307	x	x	x		x	x	x			
Cetyl Methacrylate 1618 F (CEMA 1618 F) [2495-27-4] (C16); [32360-05-7] (C18)		 n = 16, 18	-24	190-210 (64 mbar)	x		x		x	x	x			
Stearyl Methacrylate 1618 F (SMA 1618 F) [2495-27-4] (C16); [32360-05-7] (C18)		 n = 16, 18	-22	190-210 (64 mbar)	x		x		x	x	x			
Stearyl Methacrylate 18 F (SMA 18 F) [32360-05-7]			-	-	x		x		x	x	x			
Behenyl Methacrylate 1822 F (BEMA 1822 F) [32360-05-7] (C18); [16669-27-5] (C22)		 n = 18, 22	-	190-210 (64 mbar)	x		x		x	x	x			
PEG Methacrylates														
Stearyl Polyethyleneglycol Methacrylate 1100 (SPEGMA 1100) [70879-51-5]		 n = 25, m = 16, 18	-	-		x								
Behenyl Polyethyleneglycol Methacrylate 1100 (BEPEGMA 1100) [125441-87-4]		 n = 25, m = 18, 22	-	-		x								
Methyl Polyethyleneglycol Methacrylate 2000 (MPEGMA 2000) [26915-72-0]			-	-		x						x		
Hydroxies														
2-Hydroxyethyl Acrylate (HEA) [818-61-1]			-15	200	x	x	x					x		x
Hydroxypropyl Acrylate (HPA) [25584-83-2]			-7	199	x	x	x					x		x
4-Hydroxybutyl Acrylate (4-HBA) [2478-10-6]			-65	236	x	x	x							x
Hydroxyethylcaprolactone (HECLA) [110489-05-9]		 n = average 2	-52	-	x	x	x							x
Acids														
Acrylic Acid (AA) [79-10-7]			105	141	x	x	x					x	x	
Methacrylic Acid (MAA) [79-41-4]			185	162	x	x	x					x	x	

Product [CAS no.]	C^{14} BIO-based content	Chemical Structure	Polymer Tg [°C]	Bp [°C]	**Coatings** *(Automotive / Industrial)*	**Emulsions** *(Coatings / Adhesives)*	**Adhesives & Sealants**	**Paper**	**Leather / Textile**	**Oilfield**	**Lubricants**	**Construction**	**Rubber / Plastics**	**Rad / UV Cure**
Misc. Monomers														
Ureido Methacrylate 25% in MMA (UMA 25%) [86261-90-7]			-	101	x	x	x				x			
Ureido Methacrylate 50% in Water (UMA 50%) [86261-90-7]			-	101	x	x	x				x			
Dihydrodicyclopentadienyl Acrylate (DCPA) [12542-30-2]			-	81 (0.7 mbar)	x		x						x	x

C^{14} BIO-based content

We want to contribute to a world that provides a viable future with enhanced quality of life for everyone. We do so by creating chemistry for our customers and society and by making the best use of available resources. Please contact us for any further questions to sustainable product solutions.

For further information on Acrylic & Methacrylic Monomers, please visit us at basf.com

More information on sustainability at BASF:

The Mass Balance Approach

Chemical recycling of plastic waste

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED GRATIS, IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR ANY RESULTS OBTAINED. ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF OUR PRODUCTS, THE READER IS NOT RELIEVED FROM CARRYING OUT ITS OWN INVESTIGATIONS AND MAKING TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. **NEITHER WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NOR ANY GUARANTEES ARE MADE/GRANTED REGARDING PRODUCTS DESCRIBED, OR THEIR PROPERTIES, DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** IN NO CASE SHALL THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION PROVIDED BE CONSIDERED A PART OF ANY SUPPLY AGREEMENT, UNLESS THE PARTIES EXPRESSLY AGREE OTHERWISE.

Version dated 09/2021

BASF

We create chemistry